



Quality insulation
with a personal touch

TECHNICAL DATASHEET NESTAAN® POLYURETHANE FOAMS

NESTAAN® PUR40C5

Appearance	Yellowish rigid foam.
Availability	Nestaan® PUR foam is available as block, sheets/slabs or in pre cutted shape such as pipe sections and various profiles. The standard maximal width for blocks and slabs is 125 cm. The length can be ordered up to 4 meter. Other dimensions on request.
Application	General high performance insulation material to be used as core material for sandwich panels, industrial insulation such as tanks, pipes, vessels, ships, cold rooms, refrigerated trucks etc.

	Value	Unit	Method	EN13165
Density	37 - 43	kg/m ³	EN 1602	
Thermal conductivity 10°C (λi)	0,020-0,024	W/m.K	EN12667	
Initial thermal conductivity 10°C (λ _{90/90})	0,023		EN13165	
Aged, diffusion open facings (d <80 mm)	0,029		EN13165	
Aged, diffusion open facings (d 80-120 mm)	0,028		EN13165	
Aged, diffusion open facings (d >120 mm)	0,027		EN13165	
Aged, diffusion tight facings	0,025		EN13165	
Compressive strength	> 200	kPa	EN826	CS(Y)175
E-Modulus	> 6000	kPa		
Tensile strength	> 225	kPa	EN1607	TR150
E-Modulus	> 7500	kPa		
Bending strength	> 400	kPa	EN12089	
E-Modulus	> 5000	kPa		
Closed cell content	> 90	%	ISO 4590	
Dimensional stability			EN1604	
70°C/90% RV, 48 h. - length+width /thickness	<1 / <1,5	%		DS(70,90)3
-20°C, 48 h. - length+width /thickness	<0,5 / <0,5	%		DS(-20,-)2
Deformation (168 h.) under 40 kPa load at 70°C	<1,5	%		
Fire behaviour				
Euroclass	F		EN13501-1	F
German classification	B3		DIN4102-1	
Water absorption	< 2	Vol-%	EN12087	
Linear expansion coefficient	50-70 . 10 ⁻⁶	m/m.K		
Service temperature	-100 / +100	°C		
Toleration on thickness				T3



Our recommendations with regard to technical applications, whether verbal, written or through means of testing, are provided to the best of our knowledge. However, they only count as non-committal guidelines, also applicable to the possible protective rights of third parties. They do not dismiss you of the obligation to check the products supplied by us on their suitability for the intended applications or purposes. Application, usage and processing of the products happen outside of our control possibilities and therefore are your own responsibility. Nestaan does not accept any liability for damage caused by the application of our products (damage by third parties and possible consequential damages included). In case a court should conclude liability, the damage of all claims is limited only to the value of the goods that we supplied to you in relation to the damage causing project. The above according to mentioned criteria in our general sales and delivery terms.

0140-UK/201405-1